

Selective Targeting and Thermal Destruction of Live Cells Using Antibody Functionalised Gold Nanoparticles

A thesis presented for the degree of
Doctor of Philosophy

by

Dakrong Pissuwan

B.Sc. (Microbiology): Srinakharinwirot University

M.Sc. (Applied Microbiology):

King's Mongkut University of Technology Thonburi

Institute for Nanoscale Technology

Faculty of Science

University of Technology, Sydney

August 2008

Certificate of Originality

I certify that the work in this thesis has not previously been submitted for a degree nor has it been submitted as part of the requirements for a degree except as fully acknowledged within the text.

I also certify that the thesis has been written by me. Any help that I have received in my research work and the preparation of the thesis itself has been acknowledged. In addition, I certify that all information sources and literature used are indicated in the thesis.

Dakrong Pissuwan

Dakrong Pissuwan

Acknowledgements

This thesis presents the results of three and a half years of work, during which I have been supported by many people.

First, I would like to thank Prof. Michael Cortie, Director of the Institute for Nanoscale Technology at the University of Technology Sydney (UTS), who is the first of my two supervisors. I am grateful for his advice and guidance, from the initial stage of doing this research until the end. He provided me with persistent encouragement and supported me in various ways in both my study and my general life. Furthermore, I learned a lot about research from his leadership, which has inspired me to grow as a good scientist in the future. He is also a person who helped me enjoy scientific writing.

I also gratefully acknowledge the contribution of Dr Stella Valenzuela, my other supervisor. She is from the Department of Molecular and Bioscience, and provided crucial advice and guidance, particularly in biological areas. Dr Valenzuela taught me a lot about mammalian cell cultures and molecular biology techniques. I would like to thank her inspiration, great efforts and kindness in every way.

Several other people have assisted me with the experimental part of my thesis. Firstly, Dr David Xu, a past fellow student at the Institute for Nanoscale Technology, produced gold nanorods for me and taught me how to synthesize my own spherical gold nanoparticles. He also helped me with the chemistry in general. Dr Richard Wuhrer, Ms Katie McBean and Mr Mark Berkahn from the Microstructural Analysis Unit at UTS kindly assisted and supported me with the use of the scanning electron microscopes. In addition, this thesis would not have been completed without the excellent transmission electron microscope images prepared for me by Dr Murray Killingsworth (Sydney South West Pathology Service). Thank you also to undergraduate student Colin Cortie: his short vacation project in 2004 was the pathfinder on which my own project was built. Next, I want to express my gratitude to Dr Brian Reedy from the Department of Chemical and Forensic Science, and Mr Geoff Stockton (a past member of the Department of Physics and Advanced Materials) who have helped me with the laser irradiation experiments. Thank you also to Dr Catherine Miller, Dr Michael Johnson and Mr Michael Lees from the Institute for the Biotechnology of Infectious Disease at

UTS, who have provided guidance and materials for the culturing of *Toxoplasma gondii* tachyzoites.

I wish to thank past and present fellow students as well as staff of the Institute for Nanoscale Technology, including Assoc. Prof. Mike Ford, Dr Abbas Maarroof, Dr Benjamin Soule de Bas, Dr Rainer Hoft, Mrs Nadine Harris, Mr Jonathan Edgar, Mr Martin Blaber, Mr Michael Coutts, Mr Nicholas Stokes, Mr Burak Cankurtaran, and Mr Don Maclurcan for helping in so many different ways.

My special thanks go to Prof. Michael Cortie, Dr Stella Valenzuela, Ms Pat Skinner and Ms Radhika Challapalli for editing and assistance with the writing of my thesis. Thank you to Prof. Tony Moon who encouraged me to come to UTS, my parents, who have always encouraged me in my studies in the first place, and to the Institute for Nanoscale Technology for providing a scholarship and covering the tuition fees.

Finally, I am very grateful to my husband, Mr Sujin Jiracheewanun. Although we have been living a tough life while doing PhDs simultaneously, it has been one of the best experiences in our life. He has provided assistance in numerous ways: he has been a part of my research, helping me with drawing pictures and acting in a “house-husbands” role for me when I needed to spend long hours in the laboratory. When I finished my work after midnight, he was the person who walked beside me on the way home. His great patient love inspired me to complete my study.

Contents

Certificate of Originality	i
Acknowledgements	ii
Glossary of Acronyms	xix
Abstract.....	xxi
1. Introduction	1
1.1 Overview and motivation	1
1.2 Present study	2
2. Literature Review	4
2.1 Properties of gold nanoparticles.....	4
2.1.1 Chemical inertness of gold	4
2.1.2 Optical absorption properties of gold nanoparticles.....	5
2.1.3 Light scattering by gold nanospheres and gold nanorods.....	11
2.2 Gold nanoparticles in biomedical applications.....	16
2.2.1 Targeting approaches for gold nanoparticles.....	16
2.2.2 Hyperthermal therapy by gold nanoparticles.....	19
2.2.3 Drug and gene delivery by gold nanoparticles.....	24
2.3 Macrophage cells and <i>Toxoplasma gondii</i> as model cellular targets.....	27
2.3.1 Macrophage cells.....	27
2.3.2 Biology of <i>Toxoplasma gondii</i> and its tachyzoites	28
2.3.3 The transmission and infection of <i>Toxoplasma gondii</i>	30
2.3.4 Diagnosis of <i>Toxoplasma gondii</i>	33
2.3.5 Drugs against <i>Toxoplasma gondii</i>	34
3. General Experimental Methods	36
3.1 Synthesis of gold nanoparticles	36
3.1.1 Synthesis of gold nanospheres	36
3.1.2 Synthesis of gold nanorods.....	39
3.2 Conjugation of gold nanoparticles to antibodies and proteins	40

3.2.1 Conjugation of gold nanospheres to protein (BSA or antibodies)	40
3.2.2 Conjugation of gold nanorods to BSA and antibodies	42
3.3 Cell culture	43
3.3.1 Basic preparation for cell culture	43
3.3.2 Thawing and freezing mammalian cell lines	44
3.3.3 Mammalian cell culture	45
3.3.4 Parasite cell culture	46
3.4 Protein analysis	48
3.4.1 BCA protein assay	48
3.4.2 Bio-Rad protein assay	49
3.5 Cellular imaging and microscopy	50
3.5.1 Bright field and confocal microscopy	50
3.5.2 Electron microscopy	50
3.6 Cell viability	51
3.7 Laser irradiation	52
3.7.1 Green laser	52
3.7.2 Red laser	53
4. Selective Targeting of Murine Macrophage Cells Using Antibody- Functionalised Gold Nanospheres	54
4.1 Introduction	54
4.2 Experimental procedures	56
4.2.1 Preparation of gold spheres	57
4.2.2 Conjugation of gold spheres and antibody	57
4.2.3 Cell preparation and labelling	58
4.2.4 Microscopy	58
4.2.5 Irradiation by laser	59
4.3 Results and discussion	59
4.3.1 Gold-protein conjugates	59
4.3.2 Attachment of gold to target cells	64
4.3.3 Selective attachment to live cells	66
4.3.4 Laser irradiation of cells	70
4.4 Conclusions	74

5. Selective Targeting of <i>Toxoplasma gondii</i> Tachyzoites Using Antibody-Functionalised Gold Nanospheres and Inhibition of Parasite Binding to Host Cells	75
5.1 Introduction.....	75
5.2 Experimental procedures	77
5.2.1 Preparation of <i>Toxoplasma gondii</i> tachyzoites and cells.....	77
5.2.2 Labelling of tachyzoites and mammalian cells with conjugated gold nanospheres.....	78
5.2.3 Confocal microscopy and transmission electron microscopy.....	78
5.2.4 Laser irradiation	79
5.2.5 Infection of host cells with <i>Toxoplasma gondii</i> tachyzoites.....	79
5.2.6 Statistics	80
5.3 Results and discussion.....	80
5.3.1 Conjugation of gold nanoparticles with anti- <i>Toxoplasma gondii</i> (30 kDa) antibody.....	80
5.3.2 Attachment of gold-anti- <i>Toxoplasma gondii</i> 30 kDa to target tachyzoites	82
5.3.3 Selective attachment of gold-anti- <i>Toxoplasma gondii</i> 30 kDa to target tachyzoites	84
5.3.4 Laser irradiation of <i>Toxoplasma gondii</i> tachyzoites	86
5.3.5 Infectious activity of <i>Toxoplasma gondii</i> into host cells after binding with gold nanoparticles	92
5.4 Conclusions.....	96
6. Selective Targeting of Murine Macrophage Cells Using Antibody-functionalised Gold Nanorods	97
6.1 Introduction.....	97
6.2 Experimental procedures	99
6.2.1 Conjugation of gold nanorods and antibody.....	99
6.2.2 Cell preparation and cell labelling with gold nanoparticles	99
6.2.3 Laser cell irradiation.....	100
6.2.4 Thermal effect on cell death	100
6.3 Results and discussion.....	101
6.3.1 Gold nanorod characterisation	101
6.3.2 Binding of gold nanorod-antibody conjugates to cells.....	103

6.3.3 Induction of cell death by laser irradiation of cells	106
6.3.4 Non-specific binding of unconjugated gold nanorods.....	108
6.3.5 Non-selective binding of antibody-conjugated gold nanorods	110
6.3.6 Cell death in isothermal experiment.....	112
6.4 Conclusions.....	113
7. Selective Targeting of <i>Toxoplasma Gondii</i> Tachyzoites Using Antibody- Functionalised Gold Nanorods and Inhibition of Parasite Binding to Host Cells	115
7.1 Introduction.....	115
7.2 Experimental procedures	116
7.2.1 Conjugation of gold nanorods with anti- <i>Toxoplasma gondii</i> antibody ...	116
7.2.2 Cell preparation and labelling with gold nanorods	117
7.3 Results and discussion.....	118
7.3.1 Characterisation of gold nanorods and their conjugation	118
7.3.2 Labelling of gold nanorod-anti- <i>Toxoplasma gondii</i> to tachyzoites	119
7.3.3 Effect of laser irradiation on <i>Toxoplasma gondii</i> tachyzoites	122
7.3.4 Effect of functionalised gold nanorods on infectious activity of <i>Toxoplasma gondii</i> tachyzoites.....	126
7.4 Conclusions.....	128
8. Conclusions	130
9. Appendix A: Calculations and Standard Graphs.....	132
A.1 Calculation of number of BSA molecules on the surface of the 20 nm gold nanospheres	132
A.1.1 Rough calculation for molecules of BSA in gold-BSA conjugates	133
A.1.2 Rough calculation for molecules of gold nanoparticles in gold-BSA conjugates	133
A.2 Calculation of the number of spherical gold nanoparticles per cells from absorption spectrum.....	134
A.3 Statistics for infection study	135
A.4 Standard graph of BSA absorbance using Bio-Rad protein assay	147
10. Appendix B: Publications, Reports and Presentations.....	149
B.1 Journal articles.....	149
B.2 Journal and magazine reports.....	150
B.3 Oral presentations	150

B.4 Poster presentations 150

B.5 Invited seminars 151

List of Figures

Figure 2.1: Schematic illustration of surface plasmon absorption of spherical nanoparticles with the excitation of the dipole surface plasmon oscillation ..	5
Figure 2.2: Optical absorption spectra of spherical gold nanoparticles (sizes 22, 48 and 90 nm).	6
Figure 2.3: The relationship between (a) the absorption bandwidth and the nanoparticle size and (b) a linear dependent relation of the extinction coefficients of gold nanoparticles against their volume. When the radius of nanoparticles decreases in intrinsic size region or increases in extrinsic size region, there is a resulting increase in the bandwidth	8
Figure 2.4: The absorption spectrum of gold nanorods with an aspect ratio of 3.3. The weak short wavelength band at 525 nm is the transverse plasmon resonance and the long wavelength band at 740 nm is the longitudinal plasmon resonance	9
Figure 2.5: Optical properties of rod-shaped gold nanoparticles at different aspect ratios. The wavelength of light of the longitudinal resonance depends on the aspect ratio of the rods. The absorption maximum of the longitudinal band is strongly red-shifted after increasing the aspect ratio.....	10
Figure 2.6: The colours and micrographs of gold nanorods with a range of mean aspect ratios.....	11
Figure 2.7: Field lines of Poynting vector around a metallic sphere illuminated by light at the plasmon wavelength ($\lambda = \lambda_p$) and at a wavelength longer than the plasmon wavelength ($\lambda > \lambda_p$). The diameter of the cross-section for absorption is indicated as a vertical line on the left	12
Figure 2.8: (a) Light scattering of silver and gold nanoparticle suspensions of different sizes illuminated by a beam of white light (a fluorescein control sample is shown on the right), (b) the light scattering imaging of 58 nm and (c) 78 nm gold nanoparticles	13

- Figure 2.9:** The geometry arrangement of light scattering. A monochromatic light beam travels along the z axis. This beam is polarized along the direction y. The scattered light is detected by the direction r using the spherical coordinates θ and ϕ 14
- Figure 2.10:** Passive and active targeting of nanoparticles. (a) Passive targeting using the enhanced permeability and retention (EPR) effect, which exploits the increased permeability of the tumour vasculature (extravasation) to concentrate therapeutic agents. (b) Active targeting of a carcinoma by antibody-functionalized nanoparticles. Once concentrated at the target site, the therapeutic payload is released in response to light of a specific wavelength 17
- Figure 2.11:** A comparison of carcinoma cells with and without silica-gold nanoshells following laser exposure and staining with a viability dye, calcein acetoxymethylester (calcein Am). Carcinoma cells without silica-gold nanoshells (the left-hand side) were still alive. Conversely, carcinoma cells with silica-gold nanoshells showed significant cell death as seen by the dark circular zone, which corresponds to the area exposed to the laser 21
- Figure 2.12:** The NIR window and light absorption of haemoglobin and water 23
- Figure 2.13:** Controlled delivery of a chemical payload. (a) The conjugation of antibody and polymer capsule binds to the bacterial target *Micrococcus lysodeikticus*, and (b) application of laser light causes the gold nanoparticles in the shell of the capsule to heat up, (c) bursting the container and releasing the therapeutic agent in a localised area. (1) The optical extinction spectra are shown for isolated gold nanoparticles, (2) a poly-electrolyte shell containing a single layer of aggregated gold particles, and (3) a shell containing three layers of gold particles 25
- Figure 2.14:** Gel electrophoretic patterns of gold nanorod-DNA complexes with and without laser irradiation. The laser intensities used for irradiation were 100, 120, 140, 160, 180, and 200 mJ/pulse. The first lane is a reference lane showing agarose gel electrophoresis of plasmid DNA. The second lane represents gold nanorod DNA complexes without a laser 26
- Figure 2.15:** The crescent shape of *T. gondii* tachyzoites (present work) 29
- Figure 2.16:** Schematic drawing of the ultrastructures of a *T. gondii* tachyzoite. 29

Figure 2.17: The life cycle of <i>T. gondii</i> , the illustration below the horizontal bar is the development of <i>T. gondii</i> in an intermediate host. The illustration above the horizontal bar is the development of <i>T. gondii</i> in a definitive host. The three infectious stages have been shaded	31
Figure 2.18: The major pathways of transmission for <i>T. gondii</i>	32
Figure 3.1: Gold colloidal suspension, showing characteristic burgundy colour	37
Figure 3.2: The synthesis of ~20 nm spherical gold nanoparticles using the citrate reduction method.....	38
Figure 3.3: Diagram illustrating the cell freezing process using IPA bath.....	45
Figure 3.4: Diagram illustrating how protein reacts with alkaline copper II to produce copper I. Bicinchoninic acid (BCA) then reacts with the copper I, resulting in an intense purple colour detectable at around 560 nm.....	49
Figure 4.1: Schematic illustration of methods by which gold nanoparticles were attached to target cells and characterised.	57
Figure 4.2: Image of unconjugated gold nanospheres taken using an electron microscope.....	60
Figure 4.3: Absorption spectra of colloidal suspensions of citrate-stabilised gold nanospheres on which the conjugation was based showing plasmon peak ~526 nm and the red shifting effect of conjugation from 526 nm to 531 and 539 with proteins CD11b and BSA respectively.....	60
Figure 4.4: Concentration gradient of BSA/gold nanoparticle mixtures. The three tubes on the left contain insufficient BSA to stabilise the colloid when concentrated NaCl solution is added. The optimum concentration of BSA is that of the fourth tube. The fifth and sixth tubes contain excess BSA that must be removed by centrifugation and washing	61
Figure 4.5: The illustration of 20 nm spherical gold nanoparticles coated with (a) a monolayer and (b) a bi-layer of BSA at the size of 5 x 5 x 5 nm	63
Figure 4.6: Image of murine macrophage cells taken using SEM at different conditions. (a) The control sample of murine macrophage cells without gold-CD11b conjugates, (b) murine macrophage cells incubated with unconjugated gold nanoparticles, and (c) murine macrophage cells incubated with gold-CD11b conjugates with the gold nanoparticles seen as bright spots	65

- Figure 4.7:** Fluorescent (left) and transmitted light (right) images of various samples of live cells. (a) Murine macrophage (Raw 264.7) cells incubated with gold and CD11b, (b) murine macrophage cells incubated only with gold/BSA conjugates followed by exposure to 2°abFITC, (c) murine macrophage cells incubated with 2°abFITC only, (d) CHO-K1 cells incubated with gold/CD11b conjugates followed by exposure to 2°abFITC, (e) murine macrophage cells plus Au/CD11b conjugates followed by exposure to 2°abFITC, (f) murine macrophage cells incubated with CD11b followed by exposure to 2°abFITC..... 67
- Figure 4.8:** Murine macrophage cells that have been incubated with gold-CD11b and 2°abFITC particles for one hour. The gold particles appear to have been taken up into the cells by endocytosis, and a proportion of them are visible as granular green concentrations within the cell. These concentrations presumably correspond to the lysosomes that are encapsulating the particles which are still fluorescent 68
- Figure 4.9:** TEM images of murine macrophage cells incubated with gold-CD11b conjugates for (a) 1 hour and (b) 2 hours showing 20 nm gold nanospheres have been taken up into endocytic vesicles 69
- Figure 4.10:** Effect of laser irradiation on murine macrophage cells with different treatments of gold nanospheres. The dead cells are green under the fluorescent mode of the confocal microscope after staining with SYTOX green dye. Top row, no laser irradiation, bottom row following laser irradiation with 543.5 nm for 10 minutes with a laser output power of ~2.5 mW. (a & e) Cells only, no gold nanoparticles, (b & f) cells incubated with unconjugated gold nanoparticles, (c & g) cells incubated with gold-BSA conjugates, (d & h) cells incubated with gold-CD11b antibody conjugates..... 72
- Figure 5.1:** Scanning electron microscopy image of 20 nm gold nanoparticles. 81
- Figure 5.2:** Absorption spectra of conjugated and unconjugated gold nanoparticles.... 81
- Figure 5.3:** Images of *T. gondii* tachyzoites after different treatments, taken using transmission electron microscope. (a) The control sample, *T. gondii* tachyzoites without gold nanoparticles, (b) *T. gondii* tachyzoites incubated with unconjugated 20 nm gold nanospheres. (c) *T. gondii* tachyzoites labelled with gold-anti-*T. gondii* 30 kDa conjugates (images

- have been taken by Dr Murray Killingsworth, Liverpool Hospital, Sydney, Australia)..... 83
- Figure 5.4:** Fluorescent (left) and transmission (right) images of specific cell *T. gondii* tachyzoites and non-specific cells (U937). The results confirm that the gold nanospheres-anti *T. gondii* conjugates were only being attached to targeted cells (*T. gondii*). (a) *T. gondii* tachyzoites incubated with gold-anti-*T. gondii* conjugates followed by incubation with goat anti-mouse IgG secondary-FITC antibody (2°abFITC). (b) *T. gondii* tachyzoites incubated with anti-*T. gondii* antibody (anti-*T. gondii*), then incubated with 2°abFITC. (c) *T. gondii* tachyzoites incubated with gold-BSA conjugates exposed to 2°abFITC. (d) *T. gondii* tachyzoites exposed to 2°abFITC only. (e) *T. gondii* tachyzoites incubated with non-conjugated gold nanospheres following with 2°abFITC and (f) Non-specific cells U937 incubated with gold-anti-*T. gondii* conjugates followed by exposure with 2°abFITC..... 85
- Figure 5.5:** The cell death rate of *T. gondii* tachyzoites exposed to a green laser at wavelength 514 nm, 600 J/cm³. Tachyzoite samples were incubated with different concentrations of gold nanoparticles with and without conjugation to anti-*T. gondii* antibody. * Significantly different from *T. gondii* tachyzoites only and no laser irradiation (C) at P < 0.05 88
- Figure 5.6:** Comparison of the death rate of *T. gondii* tachyzoites labelled and non-labelled with gold-anti-*T. gondii* conjugates at laser energies of 900 J/cm³, 1560 J/cm³, and 2100 J/cm³ respectively 90
- Figure 5.7:** Death rate of *T. gondii* tachyzoites with and without exposure to the laser under different conditions. The power of the laser was 1800 J/cm³ and the concentration of gold nanoparticles per tachyzoite was 6.2 x 10¹⁰ NPs/dose)..... 91
- Figure 5.8:** The effect of gold-anti-*T. gondii* conjugates on invasion of host cells (CHO-K1 cells) by *T. gondii* tachyzoites for 1 hour in each treatment. * Significant inhibition of tachyzoites *T. gondii* invasion compared with non-labelled tachyzoites and tachyzoites labelled with unconjugated gold nanospheres at P < 0.05..... 93
- Figure 5.9:** The distribution of tachyzoites after incubation with different solutions for 30 minutes. (a) Tachyzoites incubated with PBS buffer, (b)

tachyzoites incubated with PBS plus 1% BSA, and tachyzoites incubated with gold-antibody conjugates. (c) The tachyzoites incubated with gold-antibody conjugates show significant clumping of cells when compared with the other treatments.	95
Figure 5.10: Clumping of tachyzoites following their labelling with gold-anti- <i>T. gondii</i> as viewed under a light microscope.....	95
Figure 6.1: Scanning electron microscope image of unconjugated gold nanorods.....	102
Figure 6.2: The absorbance spectra of conjugated and unconjugated gold nanorods. The absorption peak at ~520 nm is referred to as the transverse plasmon resonance and the peak at ~670 - 708 nm is identified as the longitudinal plasmon resonance	102
Figure 6.3: Schematic diagram demonstrating protein molecules possibly attached at the ends of gold nanorod.	103
Figure 6.4: Fluorescent (left) and transmittance (right) image of (a) murine macrophage cells stained with CD11b antibody-conjugated gold nanorods and secondary goat anti-rat IgG-FITC antibody. The bright green colour in the fluorescent image implies a distribution of antibody-conjugated gold nanorods on the cell surfaces; (b) control sample, left fluorescent and right transmittance mode, showing no staining of murine macrophage cells by the unconjugated gold nanorods and secondary goat anti-rat IgG-FITC antibody.....	104
Figure 6.5: Scanning electron microscope images of (a) control sample of murine macrophage cells and (b) murine macrophage cells stained with antibody-conjugated gold particles, seen as bright white spots.....	105
Figure 6.6: Transmission electron microscope cross-section through cell showing (a) rod being engulfed by a pseudopod prior to phagocytosis and (b) rod particles in endocytic vesicles (images courtesy of Dr Murray Killingsworth).....	106
Figure 6.7: Image of murine macrophage cells stained with propidium iodide to indicate cell death following laser irradiation. Non-labelled murine macrophage cells (left) and murine macrophage cells labelled with gold nanorod-antibody conjugates after laser irradiation (right).....	107
Figure 6.8: Comparison between the cell death rates of murine macrophage cells that had been labelled with gold nanorod-antibody conjugates and non-	

- labelled murine macrophage cells (a laser diode with $\lambda = 650$ nm was used). 108
- Figure 6.9:** Cell death of murine macrophage cells incubated with unconjugated gold nanorods, conjugated gold nanorods, and gold-BSA conjugates at 29.7 J/cm^2 (a laser diode: $\lambda = 650$ nm, 10 minutes exposure). The cell death rates of three treatments are significantly different at $P < 0.05$ 110
- Figure 6.10:** The percentage of cell death of targeted and non-targeted cells by unconjugated gold and gold-antibody conjugates of rod-shaped particles at 6.8 J/cm^2 (a laser diode: $\lambda = 650$ nm). * Significantly different from only CHO-K1 cells and CHO-K1 cells incubated with unconjugated gold particles and ** significantly from only macrophage cells at $P < 0.05$ 111
- Figure 6.11:** Isothermal survivability data for murine macrophage cells in PBS solution maintained at temperature between 45 and 60°C 113
- Figure 7.1:** Schematic illustration of method by which gold nanorods were attached to target protozoan and characterised. 117
- Figure 7.2:** Characterisation of gold nanorods. (a) Unconjugated gold nanorods imaged in a scanning electron microscope. (b) The absorbance spectra of conjugated and unconjugated gold nanorods. The absorption peak of the transverse plasmon resonance is around 520 nm and is not significantly changed by conjugation. However, the longitudinal plasmon resonance is red-shifted from 675 nm to 692 nm by conjugation. 119
- Figure 7.3:** Fluorescent (left) and transmitted light (right) images of *T. gondii* tachyzoites and U937 cells. The results confirm that the gold nanorods-anti *T. gondii* conjugates were only being attached to targeted cells (*T. gondii*). (a) *T. gondii* tachyzoites incubated with anti-*T. gondii*-gold conjugates followed by exposure to secondary goat anti-mouse IgG-FITC antibody (2°abFITC). (b) *T. gondii* tachyzoites incubated with anti-*T. gondii* antibody (anti-*T. gondii*), followed by exposure to 2°abFITC . (c) *T. gondii* tachyzoites incubated with BSA-gold conjugates following with 2°abFITC . (d) *T. gondii* tachyzoites incubated with 2°abFITC only. (e) U937 cells incubated with anti-*T. gondii*-gold conjugates and followed by exposure to 2°abFITC 121
- Figure 7.4:** The cell death rates of *T. gondii* tachyzoites that had been labelled with gold nanorod-antibody conjugates compared to that of non-labelled *T.*

<i>gondii</i> tachyzoites (The laser diode used had $\lambda = 650$ nm and a power of 100 mW).	123
Figure 7.5: Effect of temperature on the viability of <i>T. gondii</i> tachyzoites.	124
Figure 7.6: Effect of laser irradiation on <i>T. gondii</i> tachyzoites and U937 cells under various conditions. The power density of the laser was ~ 12200 J/cm ² . (Error bars correspond to standard deviation from the mean.). * Significantly different in the number of cell death from other treatments and ** significantly different from <i>T. gondii</i> tachyzoites incubated with gold-antibody conjugates after laser irradiation at $P < 0.5$	126
Figure 7.7: The percentage of CHO-K1 cells infected with <i>T. gondii</i> tachyzoites at different treatments for 1 hour.* Significant inhibition of infection compared with non-labelled tachyzoites and tachyzoites labelled with unconjugated gold nanospheres at $P < 0.05$	128
Figure A.1: Calibration graph of bovine serum albumin (BSA, 0 – 1 mg/ml) using BCA protein assay.	132
Figure A.2: Standardised graph of absorption versus number of gold nanoparticles, for different concentrations of spherical gold nanoparticles per 100 μ L. ...	134
Figure A.3: Standard graph of bovine serum albumin (BSA, 0 - 0.5 mg/ml) absorbance for analysis of protein concentration in the supernatant of gold nanosphere/antibody conjugates.	147
Figure A.4: Standard graph of bovine serum albumin (BSA, 0-0.5 mg/ml) absorbance for analysis of protein concentration in the supernatant of rod-shaped gold/antibody conjugates.	148

List of Tables

Table 3.1: The mixtures of gold nanospheres and protein used for conjugation in the experiments of Chapters 4 and 5	42
Table 3.2: The mixtures of gold nanorods and protein used for conjugation in the experiments of Chapters 6 and 7	43
Table 3.3: Details of media and materials for cell culture.....	47
Table 4.1: Cell death rates with and without gold-CD11b conjugate particles and laser irradiation.....	71
Table A.1: The percentage of <i>T. gondii</i> tachyzoites infecting host cells with and without attachment of spherical gold nanoparticles	135
Table A.2: Analysis of variance for infection percentage of <i>T. gondii</i> tachyzoites at different treatments with 0.05 significant level ($\alpha = 0.05$).	136
Table A.3: PHStat Tukey-Kramer analysis for infectious activity of <i>T. gondii</i> tachyzoites with and without labelling of spherical gold nanoparticles (at level of significance 0.05, numerator d.f. value of 4, denominator d.f. value of 16, mean square within (MSW) value of 52.742, and Q statistic value of 4.05).	136
Table A.4: The percentage of <i>T. gondii</i> tachyzoites infecting host cells with and without labelling of rod-shaped gold nanoparticles.	137
Table A.5: Analysis of variance for infection percentage of <i>T. gondii</i> tachyzoites at different treatments with 0.05 significant level ($\alpha = 0.05$).	137
Table A.6: PHStat Tukey-Kramer analysis of the infectious activity of <i>T. gondii</i> tachyzoites with and without labelling of rod-shaped gold nanoparticles (at level of significant 0.05, numerator d.f. value of 3, denominator d.f. value of 12, mean square within (MSW) value of 23.843, and Q statistic value of 3.77).	138

Table A.7: PHStat Tukey-Kramer analysis cell death rates of <i>T. gondii</i> tachyzoites after exposing to a green laser at wavelength 514 nm, 600 J/cm ³ (Chapter 5-Figure 5.5; at level of significance 0.05, numerator d.f. value of 6, denominator d.f. value of 76, mean square within (MSW) value of 13.450, and Q statistic value of 4.15).....	139
Table A.8: PHStat Tukey-Kramer analysis cell death rates of <i>T. gondii</i> tachyzoites with and without exposure to laser under different conditions. The power of laser was 1800 J/cm ³ . The concentration of gold nanoparticles per tachyzoites was 6.2 x 10 ¹⁰ NPs/does. (Chapter 5-Figure 5.7; at level of significance 0.05, numerator d.f. value of 6, denominator d.f. value of 155, mean square within (MSW) value of 13.985, and Q statistic value of 4.10).....	141
Table A.9: PHStat Tukey-Kramer analysis cell death rates of murine macrophage cells incubated with different forms of gold nanoparticles and exposed to a laser at 29.7 J/cm ² . (Chapter 6-Figure 6.9; at level of significance 0.05, numerator d.f. value of 3, denominator d.f. value of 17, mean square within (MSW) value of 122.311, and Q statistic value of 3.63).....	142
Table A.10: PHStat Tukey-Kramer analysis cell death rates of CHO-K1 and murine macrophage cells by unconjugated gold nanorods and gold nanorod-antibody conjugates at a laser energy of 6.8 J/cm ² . (Chapter 6-Figure 6.10; at level of significance 0.05, numerator d.f. value of 3, denominator d.f. value of 22, mean square within (MSW) value of 4.840, and Q statistic value of 3.55 for CHO-K1 cells and numerator d.f. value of 3, denominator d.f. value of 25, mean square within (MSW) value of 43.181, and Q statistic value of 3.52 for murine macrophage cells).....	143
Table A.11: PHStat Tukey-Kramer analysis cell death rates of <i>T. gondii</i> tachyzoites and U937 cells under various conditions at the power density of 12192 J/cm ² . (Chapter 7-Figure 7.6; at level of significance 0.05, numerator d.f. value of 10, denominator d.f. value of 101, mean square within (MSW) value of 28.371, and Q statistic value of 4.59).....	144

Glossary of Acronyms

2°abFITC	Secondary IgG antibody conjugated with FITC
AgNO ₃	Silver nitrate
AlOOH	Aluminium oxide hydroxide
Au	Gold
BCA	Bicinchoninic acid
BSA	Bovine serum albumin
Cat. No.	Catalogue Number
CD8	Cluster of differentiation 8
CD11b, CD11b-Mac1	Rat rat anti-mouse monoclonal antibody
CHO-K1	Chinese hamster ovary cells
CTAB	Hexadecyltrimethylammonium bromide, also known as cetyltrimethylammonium bromide
DMEM-F12	Dulbecco's modified Eagle's medium/Ham's nutrient mixture F-12
DMSO	Dimethyl sulfoxide
DNA	Deoxyribonucleic acid
DTC	Dithiocarbamate
EDTA	Ethylenediaminetetraacetic acid
ELISA	Enzyme-linked immunosorbent assay
EGFR	Epidermal growth factor receptor
EPR	Enhanced permeability and retention
FBS	Fetal bovine serum, alpha-immediate heat
FITC	Fluorescein isothiocyanate
GLUT1	Glucose transporter type I
HAuCl ₄	Chloroauric acid
HCl	Hydrochloric acid

HEPES	Hydroxyethylpiperazine-N'-2-ethanesulfonic acid
HER2	Human epidermal growth factor receptor 2
HNO ₃	Nitric acid
HOC	Human oral squamous cell carcinoma
IgG	Immunoglobulin G
KBH ₄	Potassium borohydride
KOH	Potassium hydroxide
MPS	Mononuclear phagocytic system
NIR	Near infrared
NPs	Nanoparticles
PBS	Phosphate buffered saline (No Ca ²⁺ and Mg ²⁺)
PCR	Polymerase chain reaction
PEG	Poly-ethyleneglycol
pI	Isoelectric point
PV	Parasitophorous vacuole
RAW264.7	Murine macrophage cell
RES	Reticuloendothelial system
RPMI1640	Roswell Park Memorial Institute media-1640
SEM	Scanning electron microscope
SKBR3	Human breast carcinoma cell
<i>T. gondii</i>	<i>Toxoplasma gondii</i>
TEM	Transmission electron microscope
U937	Human leukemic monocyte lymphoma cell line

Abstract

Precious metal nanoparticles have attracted considerable interest on account of their actual or potential applications in chemical, biological or medical analyses, and for their applications in various new types of optical devices or systems. These particles can be engineered to absorb light at a particular wavelength and they can also be chemically functionalised to bind to target cells. Active targeting of the gold particles to the site of a disease can be achieved, in principle, by attaching a suitable antibody to the surface of the gold. Localised heating arises when the affected tissue is irradiated with a laser tuned to the plasmon resonance of the nanoparticle because some of the incident laser light is converted to heat in the particle, which then flows out of the nanoparticle into the target cell. This principle is currently being explored overseas as the basis of a novel form of medical treatment for cancer.

In this thesis, I extend this concept to develop a method for selectively killing different cellular targets. I report how gold nanoparticles, either spherical or rod-shaped, were functionalised with specific antibodies so that they would selectively attach to particular target cells: murine macrophage cells and tachyzoites of the protozoan parasite *Toxoplasma gondii*. Following this, the cells were exposed to defined wavelengths and low intensities of continuous laser irradiation from a HeNe laser or a solid state diode laser. Cell viability was determined using nucleic stain dye. Exposure of target cells to specific bioconjugated gold nanoparticles resulted in the highest number of cell death compared with other treatments. In addition, another useful result, independent of the actual process of photothermal therapy, is described in this thesis. This involves the attachment of gold nanoparticle-antibody conjugates to *Toxoplasma gondii* tachyzoites, which clearly reduced their infection of host cells. Therefore, the research described provides both for an exciting and novel possibility for *in vivo* killing of any type of target cells using photothermal therapy and for a means to decrease host cell invasion by an intracellular parasite in the body.